

ENNIS ROADPLAST PRIMER P1

Product Specification

Product Code: MCAP1

Ennis Roadplast Primer P1 is formulated to be used as a primer to promote adhesion of *Ennis Roadplast* cold applied plastic products on concrete surfaces. It is a colourless liquid with a peculiar MMA smell.

Application

Ennis Roadplast Primer P1 requires the thorough incorporation of *Dibenzoyl Peroxide* (Product Code: MCAP2) prior to application on concrete surfaces. It can easily be applied by roll application. The amount of the *Dibenzoyl Peroxide* powder added will vary between 0.5% and 3.0 % by weight of *Ennis Roadplast Primer P1* depending on material temperature and road surface temperature. (Consult the table below)

| Temperature (°C) | Hardener (% by weight) | Pot Life (mins) | Curing Time (mins) |
|------------------|------------------------|-----------------|--------------------|
| 10> | 3.0 | 15 | 55 |
| 20> | 1.5 | 10 | 45 |
| 30> | 0.7 | 15 | 40 |

Coverage rate is 3 – 5 square metre per litre depending on roughness of the concrete surface.

Transport and Storage

Refer to product Material Safety Data Sheet (MSDS).

Packaging

18 L pail

Additional Information

Please contact Ennis Traffic Safety Solutions Pty Ltd if you require:

- An MSDS
- Pricing and availability
- Or more information on this product or other products in the wide range of products manufactured by Ennis Traffic Safety Solutions specifically for the roadmarking industry.

Ennis Traffic Safety Solutions Pty Ltd

29-31 Memorial Avenue

Ingleburn NSW 2565

Tel: 02 9829 4275 Fax: 02 9829 4362

Email: Enquiry@ennistraffic.com.au

All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed, and the preceding is made in lieu of all warranties, expressed or implied.